

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 707 909 A1

(12)

EUROPEAN PATENT APPLICATION

published in accordance with Art. 158(3) EPC

(43) Date of publication:

24.04.1996 Bulletin 1996/17(51) Int. Cl.⁶: **B22D 11/10, B22D 11/18**(21) Application number: **94910564.7**(86) International application number: **PCT/JP94/00513**(22) Date of filing: **29.03.1994**

(87) International publication number:

WO 95/26243 (05.10.1995 Gazette 1995/42)

(84) Designated Contracting States:

DE FR GB IT(71) Applicant: **Nippon Steel Corporation****Chiyoda-ku Tokyo 100 (JP)**


(72) Inventors:

- **HARADA, Hiroshi**
Nippon Steel Corporation
Futtsu-shi Chiba 299-12 (JP)
- **TAKEUCHI, Eiichi**
Nippon Steel Corporation
Futtsu-shi Chiba 299-12 (JP)

• **TOH, Takehiko****Nippon Steel Corporation Technical**
Futtsu-shi Chiba 299-12 (JP)• **ISHII, Takanobu****Nippon Steel Corporation Nagoya**
Aichi 476 (JP)(74) Representative: **VOSSIUS & PARTNER****Siebertstrasse 4**
D-81675 München (DE)(54) **METHOD OF CONTROLLING FLOW IN CASTING MOLD BY USING DC MAGNETIC FIELD**

(57) This invention relates to a method of controlling a flow in a casting mold in a DC magnetic field, in which the casting of steel is done continuously as a flow of molten steel discharged from a nozzle is controlled by applying a DC magnetic field having substantially uniform magnetic flux density distribution in the entire widthwise direction of a casting mold to the casting mold in the direction of the thickness thereof, characterized in that the meniscus velocity of flow on the surface of the molten steel in the casting mold is controlled within a range of 0.20 - 0.40 m/sec by regulating an ejection angle of the nozzle, position of the magnetic field and a magnetic flux density. When the meniscus velocity of flow is increased greatly, a control operation is carried out in accordance with the following equation (1): $V_p/V_o = 1 + \alpha_1 \{1 - \exp(-\beta_1 \cdot H^2)\}$ by dashing an ejection flow from the nozzle directly against a shorter wall of the casting mold, and, when the meniscus velocity of flow is increased or reduced, a control operation is carried out in accordance with the following equation (2): $V_p/V_o = 1 + \alpha_2 \{\sin(\beta_2 \cdot H) \exp(-\gamma \cdot H)\}$ by dashing an ejection flow from the nozzle against a shorter wall of the casting mold after passing it through a magnetic field zone. In equations (1) and (2) $H = 185.8 \cdot B^2 \cdot D \cdot T / (D+T) \cdot V$.

Fig.1



EP 0 707 909 A1

Description

TECHNICAL FIELD

5 The present invention relates to a continuous casting method wherein a direct current magnetic field is applied to the direction of thickness of the mold over the whole width direction to make the molten steel stream uniform, and particularly to a continuous casting method wherein the meniscus flow velocity within the mold is regulated to a specific range.

10 BACKGROUND ART

It is known that, in continuous casting, the flow of a molten steel within a mold greatly influences the quality of cast slabs and the operation. Specifically, the flow of a molten steel stream delivered through a nozzle brings slag inclusions, included in the molten steel, into a deep portion of a strand pool. The deeper the portion into which the inclusions are brought, the easier the trapping of the inclusions in a solidified shell and, hence, the higher the possibility of occurrence of defects in a cast slab. For this reason, the depth of the entry of a descending stream should be preferably as small as possible. On the other hand, regarding the surface of a molten steel, when the meniscus flow velocity is high as is observed in high-speed casting, entrainment of a powder present on the surface of the molten steel in the molten steel or an increase in a variation in molten steel surface level occurs. When the meniscus flow velocity is low, as is observed in low-speed casting, a deckle is formed on the surface of the molten steel, hindering the operation. Further, in this case, inclusions or Ar bubbles are trapped in a solidified shell to deteriorate the quality of the cast slab in its portion very near the surface thereof. For this reason, the meniscus flow velocity should be kept on a constant level. Since it is difficult to attain such a flow pattern through the regulation of the nozzle shape and the nozzle depth from the molten steel surface, several methods for regulating the flow of a molten steel within a mold by taking advantage of a direct current magnetic field have been proposed in the art.

Japanese Examined Patent Publication (Kokoku) No. 2-20349 discloses a method wherein the flow of a molten steel within a mold is regulated using a direct current magnetic field. In this method, a direct current magnetic field is allowed to act on a part of a main passage of a molten steel stream delivered through a submerged nozzle to decelerate the main stream of the molten steel, thereby preventing the entry of a descending stream into a deep portion of a strand pool. At the same time, the main stream is divided into small streams to cause agitation of the molten steel within the pool. In this method, however, since a direct current magnetic field is allowed to act on a part of the width of the mold, a stream delivered through the nozzle, in some cases, bypasses a brake band (a magnetic field band). That is, a stream directed from a place, where the brake is weak, toward the lower part of the pool occurs. This brings inclusions into a deep portion of the pool. Further, in this case, since this phenomenon is not stable, the flow of the molten steel within the mold becomes unstable, resulting in unstable agitation at the upper part of the pool. For this reason, the above method could not improve the quality of the cast slab.

Japanese Unexamined Patent Publication (Kokai) No. 2-284750 discloses a method wherein a direct current magnetic field is applied to the whole region in the width direction of the mold. According to this method, although a stream below the brake band can be brought into plug flow, the direct current magnetic field is applied to a place where braking is applied. Further, the regulation of the meniscus flow velocity is carried out by applying a direct current magnetic field to the whole mold or alternatively by applying a direct current magnetic field in a two-stage manner. A method wherein a direct current magnetic field is applied to a portion below the nozzle hole is also disclosed therein. As described below, however, the meniscus flow velocity is influenced greatly by the angle of a molten steel stream delivered through a nozzle, the position of the magnetic field, and the magnetic flux density, and, hence, even in this method, the flow of the molten steel was unstable.

Thus, although the prior art discloses methods for bringing a stream below a brake band into plug flow, it does not disclose any method for regulating the meniscus flow velocity by different means depending upon the casting speed.

DISCLOSURE OF THE INVENTION

50 The present invention provides a method wherein the depth of the entry of a descending stream of a molten steel stream is decreased and, at the same time, particularly the meniscus flow velocity on the molten steel surface is regulated according to the casting speed, thereby providing a cast slab having a very excellent surface property unattainable by the above conventional methods.

55 Specifically, the present invention provides a method for regulating the flow of a molten steel within a mold by taking advantage of a direct current magnetic field, comprising the step of carrying out continuous casting while regulating the flow of a molten steel by applying a direct current magnetic field having a substantially uniform magnetic flux density distribution over the whole width direction of the mold, characterized in that the flow velocity of a meniscus on the surface of the molten steel within the mold is regulated in a range of from 0.20 to 0.40 m/sec while applying a magnetic field.

When the flow velocity of the meniscus on the surface of the molten steel is significantly increased, the molten steel delivery angle of the nozzle and the position of the magnetic field are determined so that a stream of the molten steel delivered through the nozzle does not traverse a magnetic field zone but collides directly with a short-side wall of the mold and the magnetic flux density B is then regulated according to the following equation (1), thereby regulating the meniscus flow velocity in the above specified range:

$$V_P/V_O = 1 + \alpha_1 \{1 - \exp(-\beta_1 \cdot H^2)\} \quad (1)$$

wherein $H = 185.8 \cdot B^2 \cdot D \cdot T/(D+T)V$

wherein V_P represents the meniscus flow velocity when a magnetic field is applied, m/sec;

V_O represents the meniscus flow velocity when no magnetic field is applied, m/sec;
 B represents the magnetic flux density in the center in the direction of the height in the direct current magnetic field, T;
 D represents the width of the mold, m;
 T represents the thickness of the mold, m;
 V represents the average flow velocity of the molten steel delivered through a nozzle hole, m/sec; and
 α_1 and β_1 are constants.

In this case, V_O is a measured value, and D , T , and V are predetermined values. Therefore, the meniscus flow velocity V_P may be regulated by regulating the magnetic flux density B .

When the meniscus flow velocity is increased or decreased, the molten steel delivery angle of the nozzle and the position of the magnetic field are determined so that a stream of the molten steel delivered through the nozzle traverses a magnetic field zone and then collides with a short-side wall of the mold and the magnetic flux density is then regulated according to the following equation (2), thereby regulating the meniscus flow velocity to the above specified range:

$$V_P/V_O = 1 + \alpha_2 \{\sin(\beta_2 \cdot H) \exp(-\gamma \cdot H)\} \quad (2)$$

wherein $H = 185.8 \cdot B^2 \cdot D \cdot T/(D+T)V$

wherein α_2 , β_2 , and γ are constants.

According to the present invention, since the meniscus flow velocity is regulated by the above method, the flow of the molten steel within the mold can be properly regulated according to the casting speed, enabling the deterioration of the quality of the surface layer in a cast slab, caused by inclusions and Ar bubbles, to be surely prevented.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a diagram showing a relationship between the meniscus flow velocity and the index of defects in the surface layer of a cast slab which indicates the optimal meniscus flow velocity of the present invention;

Fig. 2 is a schematic plan view of a magnetic field coil for generating a direct current magnetic field;

Fig. 3 is a diagram showing a relationship between the parameter H and the casting speed, which indicates a parameter H necessary for bringing a molten steel stream to plug flow;

Fig. 4 is a diagram showing a relationship between the parameter H and the meniscus flow velocity in an embodiment where a stream of a molten steel delivered through a nozzle collides directly against a short-side wall of a mold;

Fig. 5 is a diagram showing a relationship between the parameter H and the meniscus flow velocity in an embodiment where a stream of a molten steel delivered through a nozzle traverses a magnetic field zone and then collides against a short-side wall of a mold;

Fig. 6 (A) is a schematic diagram showing the collision of a molten steel stream, delivered through a nozzle, directly against a short-side wall of a mold;

Fig. 6 (B) is a schematic diagram showing the traverse of a magnetic field zone by a molten steel stream, delivered through a nozzle, followed by the collision of the molten steel stream against a short-side wall of a mold;

Figs. 7 (A) to 7 (D) are a typical diagram showing a relationship between a molten steel stream, delivered through a nozzle, and a magnetic field zone;

Fig. 8 is a diagram showing an index of defect in the surface layer of cast slabs prepared in Examples 1 to 3 and Comparative Examples 1 to 3;

Fig. 9 is a diagram showing an index of defects in the interior of cast slabs prepared in Examples 1 to 3 and Comparative Examples 1 to 3;

Fig. 10 is a diagram showing an index of defects in the surface layer of cast slabs prepared in Examples 4 to 6 and Comparative Examples 4 to 6;

Fig. 11 is a diagram showing an index of defects in the interior of cast slabs prepared in Examples 4 to 6 and Comparative Examples 4 to 6;

Fig. 12 is a diagram showing an index of defects in the surface layer of cast slabs prepared in Examples 7 to 9 and Comparative Examples 7 to 9; and

Fig. 13 is a diagram showing an index of defects in the interior of cast slabs prepared in Examples 7 to 9 and Comparative Examples 7 to 9.

BEST MODE FOR CARRYING OUT THE INVENTION

The best mode for carrying out the invention will now be described.

Continuous casting can be classified roughly into three systems, i.e., low-speed casting, medium high speed casting, and high-speed casting, according to the casting speed.

In a low-speed casting process, casting of a thick material is carried out at a rate of less than about 0.8 m/min using a vertical casting machine.

In a medium-speed casting process, casting is carried out at a rate of about 0.8 to less than 1.8 m/min using a bending type continuous casting machine, a vertical bending type continuous casting machine or the like, and, in a high-speed casting process, a thin material is cast at a rate of about 1.8 to less than 3 m/min using a vertical bending type continuous casting machine or the like.

Thus, a considerable difference in casting speed is found among casting processes, resulting in a variation in meniscus flow velocity on the surface of a molten steel according to casting conditions (casting speed, size of cast slab and the like).

As described above, when the meniscus flow velocity is high, the variation in molten steel level becomes so large that a powder present on the surface of the molten steel is entrained in the molten steel, while when the meniscus flow velocity is low, inclusions or Ar bubbles are trapped in a solidified shell. In both the cases, the surface quality of the resultant cast slab is deteriorated.

Therefore, mere regulation of the meniscus flow velocity cannot provide a cast slab having an excellent surface quality.

Based on the above recognition, the present inventors have made studies on an optimal meniscus flow velocity range. Specifically, casting was carried out using an actual continuous casting machine under various casting conditions to investigate the relationship between the meniscus flow velocity and the defect in a cast slab. As a result, it has been found that, when the meniscus flow velocity is in the range of 0.20 to 0.40 m/sec, the defect of the cast slab can be significantly reduced. The results are shown in Fig. 1. As can be seen from the drawing, when the meniscus flow velocity is in the range of from 0.20 to 0.40 m/sec, the index of defects in the surface of cast slabs is not more than 1.0, indicating that a meniscus flow velocity in this range can offer improved surface quality.

Means for providing a meniscus flow velocity in the above range will now be described.

The present inventors have made a model experiment using mercury in equipment corresponding to a scale of about 1/2 of an actual machine to elucidate the influence of the angle of a molten steel delivered through a nozzle, the position of a magnetic field, and the magnetic flux density.

At the outset, a direct current magnetic field was formed, for example, by, as shown in Fig. 2, providing a pair of coils 4, 4 on opposed legs 3, 3 of a \square -shaped iron core 2 and passing a direct current through the coils 4, 4. In this case, a direct current magnetic field having a magnetic flux density, which is uniform in the width reaction, could be provided by using a magnetic pole having a width larger than the width of the mold.

Then, this direct current magnetic field was used to determine conditions for bringing a molten steel stream below the magnetic field zone applied to the molten steel into plug flow.

Basically, a higher magnetic flux density facilitates plug flowing. The present inventors have defined the minimum required magnetic flux density depending upon the amount of the poured molten steel by the following parameter H:

$$H = 185.8 \cdot B^2 \cdot D \cdot T / (D+T)V$$

wherein

B represents the magnetic flux density in the center in the direction of the height in the direct current magnetic field,

D represents the width of the mold,

T represents the thickness of the mold, and

V represents the average flow velocity of the molten steel delivered through a nozzle hole.

The parameter H represents the ratio of the electromagnetic force acting on the molten steel, due to the direct current magnetic field, to the inertial force of the molten steel stream delivered through the nozzle. The larger the B value and the smaller the V value, the larger the H value. The relationship between the parameter H and the flow velocity of a

descending stream in the vicinity of a short-side wall of a mold below the magnetic field was investigated in order to provide conditions for bringing the molten steel stream into plug flow. As a result, it has been found that, as shown in Fig. 3, the stream below the magnetic field zone can be brought into plug flow by bringing the H value to not less than 2.6 although the braking efficiency somewhat varies depending upon the molten steel delivery angle of the nozzle and the position of the magnetic field.

In Fig. 3, the casting speed in continuous casting is plotted on the ordinate, W is the flow velocity of a descending stream, in the vicinity of a short-side wall, below the magnetic field zone, and Vc is a value obtained by dividing the amount of the stream delivered through the nozzle by the horizontal sectional area of the pool.

Then, in order to learn what the meniscus flow velocity is, the present inventors have investigated the relationship between the meniscus flow velocity and the parameter H by varying the angle of a molten steel stream delivered through a nozzle, the position of a magnetic field, and the flow velocity of the molten steel with a direct current magnetic field applied. As a result, it has been found that there is a clear relationship between the parameter H and the ratio of the meniscus flow velocity Vp in the case where a magnetic field is applied, to the meniscus flow velocity Vo in the case where no magnetic field is applied, i.e., Vp/Vo, and that two tendencies are found in the above relationship.

Specifically, one of tendencies is that, as shown in Fig. 4, an increase in parameter H results only in an increase in meniscus flow velocity. The other tendency is that, as shown in Fig. 5, when the parameter H is increased, the meniscus flow velocity is first increases and then decreases.

Further, it has been found that these two tendencies depend upon whether or not a molten steel stream delivered through the nozzle traverses a region having the highest magnetic flux density in a magnetic field zone when it collides with a short-side wall of the mold.

As shown in Fig. 6 (A), when a molten steel stream 7 delivered through a nozzle 5 in a mold 1 collides against a short-side wall 1A in the mold before it traverses a magnetic field zone 6, the meniscus flow velocity ratio Vp/Vo of a meniscus flow 8 has a tendency as shown in Fig. 4.

On the other hand, as shown in Fig. 6 (B), when the molten steel stream 7 delivered through the nozzle 5 in the mold 1 traverses the magnetic field zone 6 and then collides against the short-side wall 1A of the wall, the meniscus flow velocity ratio has a tendency as shown in Fig. 5.

From the above results, the following facts have been found. In an embodiment shown in Fig. 6 (A), when the parameter H is not less than 0.3, the meniscus flow velocity Vp is clearly higher than the meniscus flow velocity Vo. On the other hand, in an embodiment shown in Fig. 6 (B), when the parameter H is less than 5.3, the meniscus flow velocity Vp is higher than the meniscus flow velocity Vo, while when the parameter H is not less than 5.3, the meniscus flow velocity Vp becomes lower than the meniscus flow velocity Vo.

In other words, it is apparent that the regulation of the position for delivering a molten steel through a nozzle, the angle of the molten steel stream delivered through the nozzle, the position of a magnetic field zone and the like are important to the regulation of the meniscus flow velocity.

In order to regulate the meniscus flow velocity so as to fall within the above optimal range, it is necessary to determine how nozzle conditions and magnetic field conditions are set with respect to the meniscus flow velocity Vo in the case where no magnetic field is applied. This can be achieved by determining the relationship between the parameter H and the ratio of the meniscus flow velocity Vp, in the case where a magnetic field is applied, to the meniscus flow velocity Vo, in the case where no magnetic field is applied, i.e., Vp/Vo. In this case, as described above, the controllability of the meniscus flow velocity varies greatly depending upon whether or not the molten steel stream delivered through the nozzle directly traverses the magnetic field. Therefore, studies should be carried out on two cases.

First, when a molten steel stream delivered through a nozzle is collided against a short-side wall of a wall before it traverses a magnetic field zone, as can be seen from Fig. 4, the meniscus flow velocity increases with increasing the parameter H. Therefore, the Vp/Vo value is an increasing function of the parameter H. Good agreement with experimental results can be attained, for example, when following equation (1) is used in the function:

$$V_p/V_o = 1 + \alpha_1 \{1 - \exp(-\beta_1 \cdot H^2)\} \quad (1)$$

In this experiment, $\alpha_1 = 2.6$ and $\beta_1 = 0.3$ were used as constant values.

On the other hand, when the molten steel stream delivered through the nozzle directly traverses the magnetic field zone, as can be seen from Fig. 5, the meniscus flow velocity first increases and then decreases with increasing the parameter H. Therefore, a function which first increases and then decreases with increasing the parameter H may be used in Vp/Vo. Good agreement with experimental results can be attained, for example, when following equation (2) is used in the function:

$$V_p/V_o = 1 + \alpha_2 \{\sin(\beta_2 \cdot H) \exp(-\gamma \cdot H)\} \quad (2)$$

In this experiment, $\alpha_2 = 6.5$, $\beta_2 = 0.63$, and $\gamma = 0.35$ were used as constant values.

The equation of parameter H is substituted for H in the equation 2 to determine the meniscus flow velocity V_p , and the magnetic flux density B is regulated to regulate the meniscus flow velocity V_p so as to fall within the range shown in Fig. 1.

The method for regulating the meniscus flow velocity will now be described in more detail.

At the outset, the meniscus flow velocity V_0 , in the case where no magnetic field is applied, is measured. In this case, for example, a metal rod is immersed in a molten steel, the load applied to the metal rod is measured with a strain gauge, and the load is converted to flow velocity to determine a desired flow velocity.

Then, in the case of application of a magnetic field, the meniscus flow velocity ratio V_p/V_0 for bringing the meniscus flow velocity V_p to the range of from 0.20 to 0.40 m/sec is determined. In this case, the target range (0.20 to 0.40 m/sec) may be previously divided by the meniscus flow velocity in the case where no magnetic field is applied. When the resultant value exceeds 1, the meniscus flow velocity should be increased in the casting operation. In this case, the equation (1) may be used. Alternatively, among parameter H values of less than 5.3, a parameter H for providing the predetermined V_p/V_0 value, that is, magnetic flux density B, may be determined using the equation (2). Which equation, the equation (1) or the equation (2), should be used depends upon the V_0 value. Specifically, when the meniscus flow velocity is small, the equation (1) is used because the degree of increase in the flow velocity is large. On the other hand, when the degree of increase in flow velocity is small, the equation (2) is used in such a region where the meniscus flow velocity is once increased and then decreased. When V_p/V_0 is less than 1, among parameter H values of not less than 5.3, a parameter H for providing the predetermined V_p/V_0 value, that is, magnetic flux density B, may be determined using the equation (2).

Thus, the application of a direct current magnetic field having a magnetic flux density distribution, which is substantially uniform in the width direction of the mold in the direction of thickness, enables the meniscus flow velocity to be regulated to the optimal range while bringing the molten steel stream below the magnetic field zone into plug flow.

The phenomenon wherein the meniscus flow velocity is once increased and then decreased can be explained as follows. In a mold, the flow velocity of a meniscus stream 8 and the depth of entry of a molten steel stream 7 delivered through a nozzle are determined by the distribution of the molten steel stream delivered through the nozzle in the case where the stream 7 delivered through a nozzle collides against a short-side wall 1A with gradual spreading and is then distributed upward or downward (see Fig. 7 (A)). In the method of the present invention, when a direct current magnetic field 6, which is substantially uniform in the width direction, is applied in the vicinity of a nozzle hole, the entry of a molten steel stream delivered through a nozzle into a lower portion of the pool is first inhibited by an electromagnetic brake. This makes the upward flow of the molten steel larger than the flow of the molten steel directed to the magnetic field zone 6, accelerating the flow in the meniscus (see Fig. 7 (B)). A subsequent increase in magnetic flux density makes the flow of the molten steel within the magnetic field zone 6 uniform, which brings the molten steel stream below the magnetic field zone 6 into plug flow (see Fig. 7 (C)). When the magnetic flux density is further increased, a region having a high magnetic flux density approaches the molten steel surface. In this case, as in the case where the molten steel stream below the magnetic field zone is brought into plug flow, a flow which rises along the short-side wall is braked. Therefore, at a certain or higher magnetic flux density, the meniscus flow velocity can be made lower than that in the case where no magnetic field is applied (see Fig. 7 (D)).

EXAMPLES

A molten low-carbon aluminum killed steel (AISI: A569-72) was poured into a mold having a size in the direction of internal width (D) of 1 to 2 m and a size in the direction of internal thickness (T) of 0.2 to 0.25 m, and casting was carried out under conditions specified in Table 1 with the average flow velocity (V) of the molten steel delivered through a nozzle being varied in a range of from 0.2 to 1.3 m/sec depending upon the casting speed.

A magnetic coil was provided on the outer periphery of the mold while taking into consideration the casting speed so that a direct current magnetic field could be uniformly applied in the width direction of the mold. Conditions for each casting speed were as follows.

(1) Low-speed casting process

Regarding common conditions, the meniscus flow velocity V_0 in the case where no magnetic field was applied was 7 cm/sec, and the magnetic flux density B for providing a parameter H of not less than 2.6 was 0.15T (tesla).

In this embodiment, the meniscus flow velocity is so low that the degree of acceleration should be large. Therefore, casting was carried out under such a condition that the meniscus flow velocity increases with increasing the magnetic flux density. That is, the molten steel delivery angle of the nozzle and the position of the magnetic field were adjusted so that a stream of the molten steel, delivered through the nozzle, did not directly traverse a high magnetic flux zone, and the H value for bringing the meniscus flow velocity to the range of from 0.20 to 0.23 m/sec was determined using the equation (1).

Specifically, in the case of a casting speed of 0.3 m/min, the magnetic flux density to be applied to the mold, that is, the magnetic flux density B necessary for increasing the meniscus flow velocity V_p to 0.22 m/sec is as follows. From the equation (1),

$$V_p/V_0 = 0.22/0.7 = 1 + 2.2 \{1 - \exp(-0.4 \times H^2)\}.$$

Therefore,

$$H = 4.3 = 185.8 \times B^2 \times 1.5 \times 0.25 / (1.5 + 0.25) \times 0.27.$$

From this,

$$B = 0.17T.$$

In this case, α_1 was 2.2, and β_1 was 0.4 with the other conditions being as given in Table 1.

Similarly, in the case of a casting speed of 0.4 m/min, the magnetic flux density was 0.16T, and the parameter H was 3.2.

Further, in the case of a casting speed of 0.5 m/min, the magnetic flux density was 0.16T, and the parameter H was 2.6.

Cast slabs prepared under the above casting conditions were investigated for defects in the surface layer and interior thereof. The results are tabulated in Table 1 and shown in Figs. 8 and 9.

For comparison, the results of investigation for defects in the surface layer and interior of cast slabs prepared under the same casting conditions except that no magnetic field was applied (1 and 2) and a nonuniform magnetic field was applied in the width direction of the mold (3) (in such a manner that a direct current magnetic field was applied in the direction of the thickness under such a condition as will provide a magnetic flux density of 0.3T using an iron core, having a coil height of 370 mm and a thickness of 370 mm, provided on a part of the width direction of the mold with the direction of the direct current magnetic field being laterally inverted) are tabulated in Table 1 and shown in Figs. 8 and 9.

As is apparent from the above table and drawings, according to the examples of the present invention, washing at the front face of a solidified shell based on the acceleration of meniscus flow velocity could prevent the trapping of inclusions in the surface layer of the cast slab, resulting in significantly reduced internal defect index and inclusion defect index in the surface layer as compared with those in comparative examples.

(2) Medium-speed casting process

Regarding common conditions, the meniscus flow velocity V_0 was 0.12 m/sec, and the magnetic flux density B for providing a parameter H of not less than 2.6 was 0.18T.

Although the meniscus flow velocity in this embodiment is higher than that in the low-speed casting process, the meniscus flow velocity should be further increased. Therefore, casting was carried out under such a condition that, in increasing the magnetic flux density, the meniscus flow velocity was first increased and, thereafter, decreased. The molten steel delivery angle of the nozzle and the position of the magnetic field were adjusted so that a stream of the molten steel, delivered through the nozzle, directly traverses a magnetic flux zone. Further, the equation (2), which is an equation applied to the case where the H is between a value which provides the maximum meniscus flow velocity and a value which provides a meniscus flow velocity identical to the case wherein no magnetic field is applied, that is, 5.3, was used to determine H (B) for bringing the meniscus flow velocity V_p to 0.31 m/sec.

Specifically, in the case of a casting speed of 0.8 m/min, the magnetic flux density B to be applied to the mold is as follows. From the equation (2),

$$V_p/V_0 = 0.31/0.12 = 1 + 5.5 \{\sin(0.6 \times H) \exp(-0.3 \times H)\}.$$

Therefore,

$$H = 3.5 = 185.8 \times B^2 \times 1.5 \times 0.25 / (1.5 + 0.25) \times 0.52.$$

From this,

$$B = 0.21T.$$

In this case, α_2 was 5.5, β_2 was 0.6, and γ was 0.3 with the other conditions being as given in Table 1.

Similarly, in the case of a casting speed of 1.0 m/min and 1.2 m/min, the magnetic flux densities were respectively 0.28T and 0.34T, and the parameters H were respectively 4.1 and 4.7.

Cast slabs prepared under the above casting conditions were investigated for defects in the surface layer and interior thereof. The results are tabulated in Table 1 and shown in Figs. 10 and 11.

For comparison, the results of an investigation for defects in the surface layer and interior of cast slabs prepared under the same casting conditions except that no magnetic field was applied (4), on a nonuniform magnetic field was applied in the width direction of the mold (5 and 6), are tabulated in Table 1 and shown in Figs. 10 and 11.

As is apparent from the above table and drawings, according to the examples of the present invention, as in the case of the low-speed casting process, the surface layer defect and the internal defect of the cast slab could be significantly reduced as compared with those in comparative examples.

(3) High-speed casting process

Regarding common conditions, the meniscus flow velocity V_0 was 0.50 m/sec, and the magnetic flux density B for providing a parameter H of not less than 2.6 was 0.29T.

Since the meniscus flow velocity in this embodiment is high, it should be decreased. Therefore, the molten steel delivery angle of the nozzle and the position of the magnetic field were adjusted so as for a stream of the molten steel, delivered through the nozzle, directly traversed a magnetic flux zone, and the equation (2) was used to determined H(B) necessary for bringing the meniscus flow velocity V_p to 0.37 m/sec.

Specifically, in the case of a casting speed of 2.0 m/min, the magnetic flux density B to be applied to the mold is as follows. From the equation (2),

$$V_p/V_0 = 0.37/0.50 = 1 + 5.5 \{ \sin(0.6 \times H) \exp(-0.3 \times H) \}.$$

Therefore,

$$H = 5.6 = 185.8 \times B^2 \times 1.1 \times 0.25 / (1.1 + 0.25) \times 1.19.$$

From this,

$$B = 0.42T.$$

In this case, α_2 was 5.5, β_2 was 0.6, and γ was 0.3 with the other conditions being as given in Table 1.

Similarly, in the case of a casting speed of 2.3 m/min and 1.8 m/min, the magnetic flux densities were respectively 0.44T and 0.43T, and the parameters H were respectively 5.8 and 6.0.

Cast slabs prepared under the above casting conditions were investigated for defects in the surface layer and interior thereof. The results are tabulated in Table 1 and shown in Figs. 12 and 13.

For comparison, the results of an investigation for defects in the surface layer and interior of cast slabs prepared under the same casting conditions except that no magnetic field was applied (9), or a nonuniform magnetic field was applied in the width direction of the mold (7 and 8), are tabulated in Table 1 and shown in Figs. 12 and 13.

As is apparent from the above table and drawings, as compared with the comparative examples, the examples of the present invention could significantly reduce the number of inclusion defects, in the surface of the cast slab, caused by powder entrainment and, further, could reduce a variation in the molten steel surface level, resulting in improved surface appearance. Further, at the same time, a stream of the molten steel below the magnetic field zone could be

brought to plug flow, resulting in significantly reduced amount of internal defects in the cast slab.

Table 1

Casting process	Cast- ing rate (m/ min)	Width of cast slab (m)	Thick- ness of cast slab (m)	Posi- tion of mag- netic field zone	Examples				Comparative Examples		
					Flow velocity of stream delivered through nozzle, V (m/sec)	Menis- cus flow veloc- ity, V Vp(m/ sec)	Index of defect in surface layer of cast slab	Index of defect in interior of cast slab	Index of defect in surface layer of cast slab	Index of defect in interior of cast slab	Remarks
Low- speed cast- ing	1	0.3	1.5	0.25	N	4.3	0.27	0.22	1.1	0.2	Magnetic field not applied
	2	0.4	1.4	0.2	N	3.2	0.27	0.22	0.9	0.3	Magnetic field not applied
	3	0.5	1.2	0.25	N	2.6	0.36	0.21	0.8	0.8	Nonuniform magnetic field applied
Moder- ate high- speed cast- ing	4	0.8	1.5	0.25	Y	3.5	0.52	0.32	0.5	0.4	Magnetic field not applied
	5	1.0	1.8	0.25	Y	4.1	0.78	0.24	0.8	0.3	Nonuniform magnetic field applied
	6	1.2	2.0	0.2	Y	4.7	0.83	0.25	0.9	0.6	Nonuniform magnetic field applied
High- speed cast- ing	7	2.0	1.1	0.25	Y	5.6	1.19	0.37	0.5	1.0	Nonuniform magnetic field applied
	8	2.3	1.0	0.25	Y	5.6	1.25	0.33	0.8	1.2	Nonuniform magnetic field applied
	9	1.8	1.2	0.25	Y	6.0	1.17	0.29	0.9	0.9	Magnetic field not applied

Note: Regarding the position of magnetic field zone given in the table,
 "N" represents that the stream of a molten steel delivered through a nozzle does not directly
 traverse a region having a high magnetic flux density, and
 "Y" represents that the stream of a molten steel delivered through a nozzle directly traverses a
 region having a high magnetic flux density.

INDUSTRIAL APPLICABILITY

As is apparent from the foregoing detailed description, according to the present invention, the meniscus flow velocity can be stably increased or decreased while bringing a molten steel stream below a magnetic field zone into plug flow according to need, enabling the meniscus flow velocity to be regulated so as to fall within a specific range (0.20 to 0.40 m/sec). This makes it possible to prepare a cast slab wherein the defects in the surface layer as well as in the interior thereof has been greatly reduced, that is, a cast slab having an improved quality. Even when the casting speed is required to be varied during casting, the present invention can flexibly cope with a change of casting conditions. Further, the molten steel stream below the magnetic field zone can be surely brought into plug flow, enabling different steels to be continuously cast without using any iron plate unlike the prior art. In addition, a deterioration in quality of the cast slab before and after varying the kind of the steel to be cast can be prevented.

Thus, the present invention is very useful in continuous casting.

Listing of Reference Numeral of Drawings

- 1 mold
- 2 iron core
- 3 leg
- 4 coil
- 5 nozzle
- 6 magnetic field zone
- 7 molten steel stream delivered through nozzle
- 8 meniscus flow

Claims

1. A method for regulating the flow of a molten steel within a mold by taking advantage of a direct current magnetic field, comprising the step of carrying out continuous casting while regulating the flow of a molten steel, delivered through a nozzle, by applying a direct current magnetic field having a substantially uniform magnetic flux density distribution over the whole width direction of the mold, characterized in that the flow velocity of a meniscus on the surface of the molten steel within the mold is regulated in a range of from 0.20 to 0.40 m/sec by regulating the molten steel delivery angle of the nozzle, the position of the magnetic field, and the magnetic flux density.
2. The method according to claim 1, wherein, when the flow velocity of the meniscus on the surface of the molten steel within the mold is increased, the molten steel delivery angle of the nozzle and the position of the magnetic field are determined so that a stream of the molten steel delivered through the nozzle does not traverse a magnetic field zone but collides directly with a short-side wall of the mold and the magnetic flux density B is then regulated according to the following equation (1), thereby regulating the meniscus flow velocity in a range of from 20 to 40 cm/sec:

$$V_p/V_o = 1 + \alpha_1 \{1 - \exp(-\beta_1 \cdot H^2)\} \quad (1)$$

wherein $H = 185.8 \cdot B^2 \cdot D \cdot T / (D+T)V$

wherein V_p represents the meniscus flow velocity when a magnetic field is applied, m/sec;

V_o represents the meniscus flow velocity when no magnetic field is applied, m/sec;
 B represents the magnetic flux density in the center in the direction of the height in the direct current magnetic field, T;
 D represents the width of the mold, m;
 T represents the thickness of the mold, m;
 V represents the average flow velocity of the molten steel delivered through a nozzle hole, m/sec; and
 α_1 and β_1 are constants.

3. The method according to claim 1, wherein, when the flow velocity of the meniscus on the surface of the molten steel within the mold is increased or decreased, the molten steel delivery angle of the nozzle and the position of the magnetic field are determined so that a stream of the molten steel delivered through the nozzle traverses a magnetic field zone and then collides with a short-side wall of the mold and the magnetic flux density is then regulated according to the following equation (2), thereby regulating the meniscus flow velocity in a range of from 0.2 to 0.40 cm/sec:

EP 0 707 909 A1

$$V_P/V_O = 1 + \alpha_2 \{ \sin(\beta_2 \cdot H) \exp(-r \cdot H) \} \quad (2)$$

wherein $H = 185.8 \cdot B^2 \cdot D \cdot T / (D+T)V$
wherein α_2 , β_2 , and γ are constants.

4. The method according to claim 2 or 3, wherein the parameter H is regulated to not less than 2.6.
5. The method according to claim 1, 2 or 3, wherein the meniscus flow velocity is regulated in a range of from 0.20 to 0.40 m/sec by regulating the position for delivering the molten steel through the nozzle, the position of the magnetic field, and the magnetic flux density.

Fig.1




Fig. 2




Fig. 3




Fig.4




Fig.5




Fig.6(A)




Fig.6(B)




Fig.7(A)




Fig.7(B)




Fig.7(C)











Fig.7(D)









INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP94/00513

A. CLASSIFICATION OF SUBJECT MATTER Int. Cl ⁵ B22D11/10, 11/18 According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) Int. Cl ⁵ B22D11/10, 11/18 Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Jitsuyo Shinan Koho 1926 - 1994 Kokai Jitsuyo Shinan Koho 1971 - 1994 Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y A	JP, A, 5-329599 (Nippon Steel Corp.), December 14, 1993 (14. 12. 93), (Family: none)	1, 5 2-4
Y A	JP, A, 5-329594 (Nippon Steel Corp.), December 14, 1993 (14. 12. 93), (Family: none)	1, 5 2-4
A	JP, A, 2-284750 (Kawasaki Steel Corp.), November 22, 1990 (22. 11. 90) & AU, A1, 5399090 & EP, A2, 401504 & BR, A, 9001945	1-5
A	JP, B2, 2-20349 (ASEA Aktiebolag), May 9, 1990 (09. 05. 90) & US, A, 4495984 & EP, B1, 40383 & BR, A, 8103058 & ES, A1, 8303148 & CA, A1, 1178779	1-5
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family		
Date of the actual completion of the international search June 7, 1994 (07. 06. 94)		Date of mailing of the international search report June 28, 1994 (28. 06. 94)
Name and mailing address of the ISA/ Japanese Patent Office Facsimile No.		Authorized officer Telephone No.

Form PCT/ISA/210 (second sheet) (July 1992)